

Alkaline Manganese Button Cell L626F

1 · Scope

The specification is applicable to the “Vinnic” brand Alkaline Manganese Button Cell L626F (Mercury free) supplied by CHUNG PAK BATTERY WORKS LTD.

2 · Kind of Products Specified

Name (Designation) : L626F

IEC Designation : /

3 · Technical Specification

3.1 Dimension :

| | | | |
|--------------|------|----------------------------------|----|
| Height (H) | 2.60 | ⁺⁰ _{-0.2} | mm |
| Diameter (Φ) | 6.80 | ⁺⁰ _{-0.2} | mm |

3.2 Average Weight : 0.32 g

3.3 Nominal Voltage : 1.5 V


3.4 Nominal Capacity : 18 mAh (Discharge at 45KΩ to 0.9V)

3.5 Typical Discharge Duration : 92 hrs (Discharge at 6.5KΩ to 0.9V)

630 hrs (Discharge at 45KΩ to 0.9V)

500 hrs (Discharge at 47KΩ to 1.2V)

3.6 The Drawing of Finished Battery :




Remark: There is deviation between part shape of “The Finished Battery Drawing” and actual product.

The Drawing of Finished Battery is for reference only.

Alkaline Manganese Button Cell L626F

3.7 Outside Shape Dimensions and Terminals :



4 · Performance

4.1 Open-circuit Voltage :

| | |
|-------------------------|---------------|
| Initial | 1.54 – 1.65 V |
| After 12 Months Storage | 1.51 – 1.65 V |

4.2 Service Out-put :

| Load Resistance | 6.5 KΩ | 45 KΩ | 47 KΩ |
|--|--------------|--------------|--------------|
| Discharge Method | Continuously | Continuously | Continuously |
| End-point Voltage | 0.9 V | 0.9 V | 1.2 V |
| Minimum Duration (Initial) | 85 Hrs | 570 Hrs | 450 Hrs |
| Minimum Duration (After 12 Months Storage) | 77 Hrs | 515 Hrs | 410 Hrs |

Remark : The word “ initial ” is applicable to the products elapsed three months or less after production.

4.3 Comparison Table For Different resistance Discharge Capacity

| Discharge Resistance | Discharge Method | End Voltage | Capacity |
|----------------------|------------------|-------------|----------|
| 6.5KΩ | Continuously | 0.9V | 18 mAh |
| 45KΩ | Continuously | 0.9V | 18 mAh |

4.4 High Temperature Electrolyte Leakage Resistance :


No deformation and no external electrolyte leakage shall be observed.

4.5 Expiry period : One year .

Alkaline Manganese Button Cell L626F

5 · Brand and packaging

5.1 Appendix 1: Standard and Packaging




Alkaline Manganese 100PCS Per Display Pallet

16000 PCS Per Display Carton

Button Cell L626F

White Insulating Pallet Measure : 130X123.5X11 mm

Carton Measure : 270X260X129 mm



Goods Dimension:

Height : 1090mm

Length : 1093mm

Width : 790mm

Wooden Pallet:

Pallet Height : 90mm

Pallet Measure : 1100X800mm

Weight :

Pallet Weight : 16.7 kgs

Net Weight : 633.6 kgs

Gross Weight With Pallet : 720.0 kgs

Quantity :

1 Layer = 12 Cartons

8 Layers X 12 Cartons =

96 Cartons / Pallet

5.2 Any specific design and packing requirements will be accommodated as required.

Alkaline Manganese Button Cell L626F

6 · Safety instructions

| Warning | Danger |
|---|---|
| ① Don't throw the batteries into fire or heat the batteries. | This may cause the batteries to disrupt or ignite. |
| ② Don't directly solder the batteries. | This may damage their insulating tapes and protective installation. |
| ③ Don't insert and use batteries with the \oplus & \ominus electrode inverse. | This can damage the batteries for being force charged, even may cause leakage, heat generation , disrupt, explosion or ignition. |
| ④ Don't short-circuit the positive and negative terminals of a battery. | This may cause heat generation, leakage, explosion, fire and personal injury. |
| ⑤ Don't expose the batteries to water. | This can cause heat generation or rust. |
| ⑥ Don't charge and force discharge batteries. | This may cause leakage, heat generation, even explosion and ignition. |
| ⑦ Don't disassemble or damage the external tubes of the batteries or modify the batteries(stack-up batteries) etc. | This easily results in short-circuit, leakage, even ignition. |
| ⑧ Store unused batteries in their original packaging away from metal objects. | This can cause battery short-circuiting which may result in venting, leakage, and explosion and personal injury. |
| ⑨ Don't crush, puncture, or otherwise mutilate to deform batteries. | This may cause venting, leakage, explosion and personal injury. |
| ⑩ Immediately stop using the batteries if leakage, discolor or etc. with them are detected. | This may cause accidents to occur. |
| ⑪ Don't drop or strongly strike the batteries. | This may result in leakage, heat generation, disrupt, even ignition. |
| ⑫ To avoid using at high temperature and high humidity ambient. | This may cause batteries early damage. |
| ⑬ a. Be sure to use the batteries within a temperature range from 0°C to 40°C. b. Be sure to storage the batteries within a temperature range at 20±5°C. | a. Use the batteries beyond the temperature range may cause leakage, heat generation, impaired performance, and shortening of service life of the batteries. b. Storage the batteries beyond the temperature range may cause heat generation, impaired performance, and shortening of service life of the batteries. |
| ⑭ Don't use old batteries with new ones. | Some batteries may be over-discharged. This can result in venting, leakage, explosion and personal injury. |
| ⑮ Don't use our batteries with any other type or brand of batteries. | Mixed-matching of batteries may result in heat generation, leakage or explosion. |
| ⑯ Remove batteries from equipment if it is not to be used for an extended period of time. | When batteries beyond expiry period, electrolyte leakage may occur causing damage to the equipment. |
| ⑰ Exhausted batteries should be immediately removed from equipment. | When discharged batteries are kept in the equipment for a long time, electrolyte leakage may occur causing damage to the appliance and/or personal injury. |
| ⑱ Keep the batteries out of the reach of children. | To avoid being swallowed. If swallowed, Please see doctor immediately. |
| ⑲ Don't allow children to replace batteries without adult supervision. | This may cause wrong operation, even may occur accident. |
| ⑳ Please use batteries within expiry period. | When batteries beyond expiry period, electrolyte leakage may occur causing damage to the equipment. And may impair batteries performance. |
| ㉑ Don't take batteries by hand directly. Please wear finger cots. | This may cause rust. |
| ㉒ Don't take batteries with iron tweezer. Please use plastic tweezer. | This can cause battery short-circuiting which may result in heat generation , leakage, and explosion. |

Alkaline Manganese Button Cell L626F

Appendix 1 : Test

1. Storage and Test Conditions for Samples

Unless otherwise specified, the storage conditions for samples shall be, as a general rule, at the temperature of $20\pm 2^{\circ}\text{C}$ and the humidity of $55\pm 20\%$.

2. Measuring Instruments

2.1 Voltmeter : The accuracy of the measuring equipment shall be $\leq 0.25\%$ and the precision shall be $\leq 50\%$ of the value of the last significant digit. The internal resistance of the measuring instrument shall be $\geq 1\text{M}\Omega$.

2.2 Load Resistance : The load resistance shall include all of the external circuit, and its allowance shall be within $\pm 0.5\%$.

2.3 Caliper : The caliper shall be the one having precision of 0.02 millimeters or the one having the same or superior precision to this.

3. Test Method

3.1 Dimensions : Measurements shall be made by use of the calipers.

3.2 Appearance : Examination shall be carried out by visual inspection .

3.3 Open-circuit Voltage : Measurements shall be carried out before the start of discharge of the sample by use of the voltmeter .

3.4 Service Out-put

Discharge Start Time : After leaving in an atmosphere at a temperature of $20\pm 2^{\circ}\text{C}$ for at least 8 hours or more .

Discharge Method : As defined in 4.2 , page 2 .

Discharge End-point : The instant when the closed-circuit voltage has reached below the end-point voltage(as defined in 4.2, page 2).

3.5 High Temperature Electrolyte Leakage Resistance



The following conditions shall be adopted for the test :

- (1) Test temperature and humidity : $45\pm 2^{\circ}\text{C}$, below 70%RH .
- (2) Test period : Leave to stand still 30 days .

Alkaline Manganese Button Cell L626F

Appendix 2 : Discharge Characteristics

Standard Discharge Curve :



Alkaline Manganese Button Cell L626F

Temperature Characteristic :

