




## SPECIFICATIONS

### Sealed Rechargeable Nickel Cadmium Ni-CD 750mAh 1/2 Sub C





**MODEL No:** NC12SC750

**Description:** 750mAh 1/2SC SIZE Ni-Cd



**Specifications**

|   |           |           |            |
|---|-----------|-----------|------------|
| Nominal Capacity                              |           | 750 mAh   |            |
| Nominal Voltage                               |           | 1.2 V     |            |
| Charge current                                | Standard  | 75mA      |            |
|   | Quick     | 225mA     |            |
|   | Fast      | 750mA     |            |
| Charge time                                   | Standard  | 14~16 Hrs |            |
|   | Quick     | 4.0 Hrs   |            |
|   | Fast      | 1.3Hrs    |            |
| Ambient Temperature                           | Charge    | Standard  | 0°C~35°C   |
|   |           | Quick     | 10°C~35°C  |
|   |           | Fast      | 10°C~35°C  |
|   | Discharge |           | -30°C~60°C |
|   | Storage   |           | -30°C~35°C |
| Internal Impedance(mΩ)<br>(Upon fully charge) |           | Max ≤ 30  |            |
| Weight  |           | 24.3g     |            |





## SPECIFICATIONS

### Sealed Rechargeable Nickel Cadmium Ni-CD 750mAh 1/2 Sub C

#### 2. PERFORMANCE

Unless otherwise stated, tests should be done within one month of delivery under the following conditions:

Ambient Temperature: T:  $20 \pm 5^{\circ}\text{C}$

Relative Humidity:  $65 \pm 20\%$

| Test Item  | Test Conditions  |                       |      |                       | Requirements                      |
|--|--|-----------------------|------|-----------------------|-----------------------------------|
| (1) <b>Standard Charge</b>   | Charge is conducted continuously for 16 hours at the constant current of 75mA (0.1C) after pre-discharge at the constant current of 150mA (0.2C) up to a cut-off voltage of 1.0V/cell  |                       |      |                       |                                   |
| (2) <b>Open-circuit Voltage</b>  | Voltage between terminals of the charged battery specified in item (1) is measured after rest for 1 hour   |                       |      |                       | $\geq 1.25\text{V}$               |
| (3) <b>Capacity (0.2C)</b>   | Capacity of the charged battery specified in item (1) is measured at 150mA (0.2C) up to a cut-off voltage of 1.0V after rest for 15 minutes. If the discharge time doesn't reach the specified value, the test may be carried out further twice, up to three times in total.     |                       |      |                       | $\geq 750\text{mAh}$              |
| (4) <b>High rate discharge(1C)</b>   | Discharge time of the charged battery specified in item (1) is measured at 750mA (1C) up to a cut-off voltage of 1.0V after rest for 15 minutes. If the discharge time doesn't reach the specified value, the test may be carried out further twice, up to three times in total. |                       |      |                       | $\geq 54\text{minutes}$           |
| (5) <b>Fast charge (1C)</b>  | Charge: 750mA (1C) $\times$ 1.3 hours (charging Cut off = $-\Delta$ V=5~10mV/cell or Temp.Cut off=50°C)  |                       |      |                       |                                   |
| (6) <b>Trickle charge current</b>  | 24.75mA (0.033C)~37.5 mA (0.05C)   |                       |      |                       |                                   |
| (6) <b>Charge retention</b>  | Capacity of the charged battery specified in item (1) is measured at 150mA(0.2C) up to a cut-off voltage of 1.0V after rest for 28 days at 20°C.   |                       |      |                       | $\geq 70\%$                       |
| (7) <b>IEC Cycle life</b><br>(IEC61951-1<br>(2003)<br>7.4.1.1)   | Cycle No   | Charge                | Rest | Discharge             | $\geq 500$                        |
|  | 1  | 0.1C $\times$ 16h     | None | 0.25C $\times$ 140min |                                   |
|  | 2-48   | 0.25C $\times$ 190min | None | 0.25C $\times$ 140min |                                   |
|  | 49   | 0.25C $\times$ 190min | None | 0.25C to 1.0v         |                                   |
|  | 50   | 0.1C $\times$ 16h     | 1-4h | 0.2C to 1.0v          |                                   |
| Cycles 1 to so shall be repeated until the discharge duration on any 50 <sup>th</sup> cycle becomes less than 3h |  |                       |      |                       |                                   |
| (9) <b>Accelerated cycle life</b>  | Charge: 750mA(1C) $\times$ 1.3 hours (charging Cut off = $-\Delta$ V=5~10mV/cell or Temp.Cut off=50°C) ;Discharge: 750mA(1C) to 1.0V/cell,end-of:70% nominal capacity  |                       |      |                       | $\geq 400$                        |
| (10) <b>Safety valve operation</b>   | Forced discharge is conducted for 60 minutes at a constant current of 750mA (1C) after pre-discharge at a constant current of 150mA(0.2C) up to 0V   |                       |      |                       | Leakage,<br>No explode or disrupt |

Nc12sc750\_spec\_17 P.2/3

*Notice: Unless duly signed and stamped, the information (subject to change without prior notice) contained herein this document is for reference only and should not be used as a criterion for product guarantee or warranty.*



**SPECIFICATIONS**  
**Sealed Rechargeable Nickel Cadmium**  
**Ni-CD 750mAh 1/2 Sub C**

|                                  |   |  |
|----------------------------------|---|--|
| (11) <b>Leakage</b>              | Fully charged at 375mA ( 0.5C ) for 2.4 hour stand for 14 days  | No leakage nor deformation   |
| (12) <b>Vibration Resistance</b> | Charge the battery 0.1C 16hrs, then leave for 24hrs, check Battery before/after vibration,<br>Amplitude 1.5mm<br>Vibration 3000 CPM<br>Any direction for 60mins.            | Change of voltage should be under 0.02V/cell, Change of impedance should be under 5 milli-ohm/cell   |
| (13) <b>Impact Resistance</b>    | Charge the battery 0.1C 16hrs<br>Then leave for 24hrs, check bat-before/after dropped,<br>Height 50cm<br>Wooden board (thickness 30mm)<br>Direction not specified, 3 times. | Change of voltage should be under 0.02V/cell<br>Change of impedance should be under 5 milli-ohm/cell |

3. EXTERNAL APPEARANCE

The cell/battery shall be free from cracks, scars, breakage, rust, discoloration, leakage nor deformation.

4. CAUTION

- (1) Reverse charging is not acceptable.
- (2) Charge before use. The cells/batteries are delivered in an uncharged state.
- (3) Do not charge/discharge with more than our specified current.
- (4) Do not short circuit the cell/battery. Permanent damage to the cell/battery may result.
- (5) Do not incinerate or mutilate the cell/battery.
- (6) Do not solder directly to the cell/battery.
- (7) The life expectancy may be reduced if the cell/battery is subjected to adverse conditions like: extreme temperature, deep cycling, excessive overcharge/ over-discharge.
- (8) Store the cell/battery uncharged in a cool dry place. Always discharge batteries before bulk storage or shipment.